

Multifunctional geotextiles for separation, filtration and protection

Secutex® PP coloured / PES



NAUE GmbH & Co. KG
Gewerbestrasse 2
32339 Espelkamp-Fiestel, Germany

Phone: +49 5743 41-0 · Fax: +49 5743 41-240
E-Mail: info@naue.com · Internet: www.naue.com

Product description:

Single-layered needle-punched staple fibre nonwoven geotextiles

Property	Test method*	Unit	R 404	R 504	R 804	R 1204
Raw material	-	-	polypropylene (PP), coloured / Polyester (PES)			
Mass per unit area	EN ISO 9864	g/m ²	400	500	800	1,200
Thickness	EN ISO 9863-1	mm	3.6	4.1	5.4	8.0
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	8.5 / 14.0	11.0 / 18.0	16.5 / 32.0	24.0 / 48.0
Elongation at max. tensile strength, md / cmd**	EN ISO 10319	%	80 / 50	80 / 50	80 / 50	80 / 50
Puncture force	EN ISO 12236	N	1,800	2,300	3,600	6,200
Displacement at static puncture strength	EN ISO 12236	mm	50	50	50	50
Characteristic opening size	EN ISO 12956	mm	0.12	0.11	0.09	0.08
Water permeability						
- V _I H ₅₀ -Index	EN ISO 11058	m/s	8.5 x 10 ⁻²	7.5 x 10 ⁻²	4.5 x 10 ⁻²	2.8 x 10 ⁻²
- Flow rate _{H50}		l/sm ²	85	75	45	28
Water flow capacity (h/h, l=1)						
- transmissivity at 2 kPa	EN ISO 12958	m ² /s	8 x 10 ⁻⁵	9 x 10 ⁻⁵	1 x 10 ⁻⁴	1 x 10 ⁻⁴
- flow off capacity at 2 kPa		l/(ms)	8 x 10 ⁻²	9 x 10 ⁻²	1 x 10 ⁻¹	1 x 10 ⁻¹
Detector tested	-	-	yes	yes	yes	yes
Roll dimensions, width x length	-	m x m	5,80 x 100	5.80 x 50	5.80 x 50	5.80 x 50

*based on, **md = machine direction, cmd = cross machine direction

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.